



7-11-07

AK/IFW

PTO/SB/21/(09-04)

Approved for use through 07/31/2006. OMB 0651-0031

U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

**TRANSMITTAL
FORM**

(to be used for all correspondence after initial filing)

Total Number of Pages in This Submission

Application Number

10/678,725

Filing Date

October 3, 2003

First Named Inventor

Robert C. Lam

Art Unit

1771/Conf. #6124

Examiner Name

Peter Y. Choi

Attorney Docket Number

01170/00078

ENCLOSURES (Check all that apply)

Fee Transmittal Form



Fee Attached



Amendment/Reply



After Final



Affidavits/declaration(s)



Extension of Time Request



Express Abandonment Request



Information Disclosure Statement



Certified Copy of Priority Document(s)

Reply to Missing Parts/
Incomplete ApplicationReply to Missing Parts
under 37 CFR 1.52 or 1.53

Drawing(s)



Licensing-related Papers



Petition

Petition to Convert to a
Provisional Application

Power of Attorney, Revocation



Change of Correspondence Address



Terminal Disclaimer



Request for Refund



CD, Number of CD(s) _____

☐ Landscape Table on CD

After Allowance Communication to TC

Appeal Communication to Board
of Appeals and InterferencesAppeal Communication to TC
(Appeal Notice, Brief, Reply Brief)

Proprietary Information



Status Letter

Other Enclosure(s) (please identify
below):

Return Postcard

Remarks

SIGNATURE OF APPLICANT, ATTORNEY, OR AGENT

Firm Name

Emch, Schaffer, Schaub & Porcello Co., L.P.A.

Signature

Printed name

Patrick P. Pacella

Date

Reg. No.

25,463

CERTIFICATE OF TRANSMISSION/MAILING

I hereby certify that this correspondence is being facsimile transmitted to the USPTO or deposited with the United States Postal Service with sufficient postage as first class mail in an envelope addressed to: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450 on the date shown below:

Signature

Typed or printed name

Kathy A. Burgess

Date

7/10/07

This collection of information is required by 37 CFR 1.5. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.11 and 1.14. This collection is estimated to 2 hours to complete, including gathering, preparing, and submitting the completed application form to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

If you need assistance in completing the form, call 1-800-PTO-9199 and select option 2.



01170/00078

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re the application of:

Robert C. Lam

Serial No: 10/678,725

Filed: October 3, 2003

For: ELASTIC AND POROUS FRICTION MATERIAL WITH HIGH
AMOUNTS OF FIBER

Exr. Peter Y. Choi

Art Unit: 1771

Confirmation No.: 6124

Commissioner of Patents
and Trademarks
Washington, D.C. 20231

July 9, 2007

RESPONSE

Sir:

In response to the Final Office Action mailed April 25, 2007, please amend
the above-identified patent application as follows:

1. (Canceled).

2. (Previously Presented) The friction material of claim 14 wherein the fibrous base material comprises about 80% by weight fibers and about 20% by weight filler.

3. (Canceled)

4. (Previously Presented) The friction material of claim 14 wherein the fibrous base material is a non-woven fibrous material.

5. (Previously Presented) The friction material of claim 14, wherein the fibrous base material is a woven fibrous material.

6. (Canceled)

7. (Previously Presented) The friction material of claim 14, wherein the fibrous base material has an average pore diameter of about 5 to about 8 μm .

8. (Canceled)

9. (Previously Presented) The friction material of claim 14, wherein the resin comprises at least one of: phenolic resin, at least one modified phenolic resin, at least one silicone resin, at least one modified silicone resin, at least one epoxy resin, at least one modified epoxy resin, or mixture of the above.

10. – 13. (Canceled)

14. (Previously Presented) A friction material comprising a fibrous base material wherein the fibrous base material comprises about 75% to about 85%, by weight, fibers and about 15% to about 25%, by weight, fillers based on the weight of the fibrous base material, wherein the fibrous base material has an average voids volume from about 50% to about 85%, wherein the fibrous base material is impregnated with a resin, and wherein the fibrous base material comprises about 35 to about 45%, by weight, of a less fibrillated aramid fiber; about 5 to about 15%, by weight, cotton fibers, about 2 to about 20%, by weight, carbon fibers.

15 – 16. (Canceled)

17. (Currently Amended) A friction material comprising a fibrous base

material wherein the fibrous base material comprises about 75% to about ~~85~~ 85% by weight, fibers and about 15% to about 25%, by weight, fillers based on the weight of the fibrous base material, wherein the fibrous base material has an average voids volume from about 50% to about 85%, wherein the fibrous base material is impregnated with a resin, and wherein the fibrous base material comprises, by wt., from about 15 to about 25% cotton fibers, about 40 to about 50% aramid fibers, 10 to about 20% carbon fibers.

18. (Previously Presented) the friction material of claim 14 wherein the fibrous base material includes about 20 to about 70% by weight of the resin.

19. (New) A friction material comprising a fibrous base material wherein the fibrous base material comprises about 75% to about 85%, by weight, fibers and about 15% to about 25%, by weight, fillers based on the weight of the fibrous base material, wherein the fibrous base material has an average voids volume from about 50% to about 85%, wherein the fibrous base material is impregnated with a resin, and wherein the fibrous base material is a woven fibrous material.